

<b>CHEMICAL ANALYSIS</b>	
<b>Contents</b>	<b>Weight %</b>
TiO <sub>2</sub>	57.71
Maximum Moisture	00.50

<b>MINERALOGICAL ANALYSIS</b>			
<b>Constituent</b>	<b>Weight %</b>	<b>Weight %</b>	<b>Weight %</b>
Ilmenite	64.30		
Altered Ilmenite	24.96		
Monazite	00.15		
Garnet	00.96		
Others	03.98		
Total Magnetics		94.35	
Rutile	04.74		
Zircon	00.91		
Total Non-Magnetics		05.65	
Total Heavies			100.00

<b>SIZE DISTRIBUTION</b>			
<b>BSS Mesh Size</b>	<b>Microns</b>	<b>Weight %</b>	<b>Cumulative % (Retained)</b>
+60	+250	02.75	02.75
+100	+150	36.83	39.58
+150	+106	40.85	80.43
+170	+90	10.23	90.66
+200	+75	06.80	97.46
+240	+63	02.10	99.56
-240	-63	00.44	
Total		100.00	

  
CHEMIST

  
CHEMIST  
Chemist